

Nr.
 Unique identification code of product-type
 Trademark **8 mm Planibel Clearvision Annealed**
 Intended use/es **Basic soda lime silicate glass intended to be used in buildings and construction work**
 Manufacturer **AGC Glass Europe - Avenue Jean Monnet 4 - 1348 Louvain-la-Neuve - Belgium**
 Harmonized standard **EN 572-9:2004**
 Notified body/ies **0336 1154 1174**

Declared performance/s

Essential characteristics	AVCP systems	Performance
Safety in case of fire		
Resistance to fire	1	NPD
Reaction to fire	3, 4	A1
External fire performance	3, 4	NPD
Safety in use		
Bullet resistance	1	NPD
Explosion resistance	1	NPD
Burglar resistance	3	NPD
Pendulum body impact resistance	3	NPD
Resistance against sudden temperature changes and temperature differentials : [K]	4	NPD
Wind, snow, permanent and imposed load resistance	4	NPD
Protection against noise		
Direct airborne sound reduction : Rw (C;Ctr) [dB]	3	32 (-1;-2)
Energy economy and heat retention		
Thermal properties : U value [W/(m ² .K)]	3	5.6
Light transmittance : τ _v	3	0.91
Light reflectance : ρ _v / ρ' _v	3	0.08 / 0.08
Solar direct transmittance : τ _e	3	0.90
Solar direct reflectance : ρ _e / ρ' _e	3	0.08 / 0.08

NPD: No Performance Determined

The performance of the product identified above is in conformity with the set of declared performance/s. This declaration of performance is issued, in accordance with Regulation (EU) N° 305/2011, under the sole responsibility of the manufacturer identified above. Signed for and on behalf of the manufacturer by:

(name and function)	At (place) on (date of issue)	(signature)
Enrico Ceriani Vice President Primary Glass Building & Industrial Division	Louvain-la-Neuve 25/01/2024	

1 8 mm Planibel Clearvision Annealed

Glass performance data simulation

wb_sunny Light properties - EN 410

Light transmittance : τ_v [%]	91
External light reflection : ρ_v [%]	8
Internal light reflection : ρ_{vi} [%]	8
Colour rendering index : Ra [%]	100

battery_charging_full Energy properties - EN 410

Total solar energy transmittance : g [%]	90
External energy reflection : ρ_e [%]	8
Internal energy reflection : ρ_{ei} [%]	8
Direct energy transmission : τ_e [%]	90
Total energy absorption : α_e [%]	2
Shading coefficient : SC	1.03
UV transmission : τ_{uv} [%]	81
Selectivity	1.01

thermometer_quart Thermal properties - EN 673

Thermal transmittance (vertical glazing) : U value [W/(m ² .K)]	5.6
--	-----

volume_up Acoustic properties

Direct airborne sound reduction - EN 12758 : R_w (C;Ctr) [dB]	32 (-1;-2)
---	------------

security Safety properties

Resistance to fire - EN 13501-2	NPD
Reaction to fire - EN 13501-1	A1
Bullet resistance - EN 1063	NPD
Burglar resistance - EN 356	NPD
Pendulum body impact resistance - EN 12600	NPD
Explosion resistance - EN 13541	NPD

line_weight Thickness and weight

Nominal thickness : [mm]	8.0
Weight : [kg/m ²]	20

1. The sound reduction indexes correspond to glazing with dimensions 1230 mm by 1480 mm according to EN ISO 10140-3 and are tested in laboratory conditions. In-situ performances may vary according to the effective glazing dimensions, supporting system, installation, environment, noise sources etc. The accuracy of the given indexes is +/- 1 dB.



Glass Configurator
Calculation software verified by INISMA
EN 410 and EN 673
Report n° 2018B COU 35741



Several AGC products are now available in Low-Carbon Glass version. The Low-Carbon Glass version does not affect the properties of the above glass configuration. For more info about the AGC Low-Carbon Glass range, please visit our YourGlass page.

The AGC Glass Configurator is a simulation tool providing a performance analysis for the limited purpose of assisting the user in evaluating the performance of the glass configuration identified in this report. The interpolated performance is only applicable for glass products manufactured or processed by AGC. It does not replace an official Declaration of Performance and therefore may contain some variations, although AGC has made every effort to verify the reliability of this simulation tool. The user assumes any risk relating to the results provided by the tool and is solely responsible for the selection of the appropriate glass configuration for the user's application.

This document is for informative purposes only and in no way implies acceptance of any order by the AGC Group. Please consult the Specific Conditions of Use for the calculation standards that are used, the INISMA test report number and the accuracy of the values.

AGC makes no express or implied warranty of any kind with respect to the Glass Configurator. There are no warranties of merchantability, non-infringement or fitness for any particular purpose and no warranty shall be implied by operation of law or otherwise. In no event shall AGC be liable for direct, indirect, consequential or incidental damages of any kind relating to or resulting from the use of the Glass Configurator.